Sinops Limited

5-B, Redlake, Road, Pedmore, Stourbridge, West Midlands DY9 ORU



DATA SHEET

FLEXIBLE METAL CORNER TAPE

DESCRIPTION & APPLICATION

Special jointing Kraft paper with two flexible parallel galvanised metal strips attached to help making sharp, reinforced edges to corners when plastering.

ADVANTAGES

With high flexibility this product can be used instead of the more traditional paper metal flex tape and metal corner head

PACKAGING

Each roll is boxed singly, the box can be then used as a dispenser.

A carton consists of 11 boxes/rolls of tape.

DIRECTIONS

Prior to use ensure that the surface is clean and completely free of dirt and grease.

Using a drywall taping knife, apply joint compound to drywall, forming the inside or outside corner, Cut the Flexible Metal Corner Tape to the desired length, fold down the centre and press to bed into the joint compound with the metal side against the wall.

Remove the extra compound with the taping knife and allow to dry.

Apply a full coat of compound over the Flexible Metal Corner then feather coat slightly beyond the taping coat then leave to dry and smooth with a wet sponge, if necessary.

For inside corners, apply compound to one side only and the leave to dry, then cover the other side. Then apply another coat of compound feathering slightly beyond the prior coat, leave to dry and smooth with a wet sponge, if necessary.

If unsure of product suitability then testing on a non-critical area should be carried out prior to full scale application

TEST DATA		Standard	Test
Length (m)		30m +/-0.3	30.1m
Width (mm)		50mm +/- 1	50mm
Paper Mass (g/m)		7.2g/m +/0.2	7.0mm
Steel Strip width (mm)		12.5mm +/- 0.5	12.5mm
Steel Strip thickness (mm)		0.38mm +/- 0.03	0.38mm
Steel Strip Gap (mm)		1.50mm	1.50mm
Application Temperature		5°C to 30°C	n/a
Tensile paper strength (N/m)	warp	> 5,200	6,580
	weft	> 4,800	5,790
Tensile paper strength (N/m) (In water for 10 hours)	warp	> 1,400	1,760
	weft	> 1,100	1,480
Adhesive Strength between paper & steel (dipped in 25 °C water for 24hrs)		Remains fully intact	Remains fully intact

Signed By:

-Name:

Richard Dunn

Position:

Managing Director

Date:

05 June 2017

This delaration is the responsibility of the importer
Sinops Limited, 5-B, Redlake, Road, Pedmore, Stourbridge, West Midlands DY9 ORU